

Laminate	Type	Tg	Td	Dk	Df	Flammability UL94
Isola						
185HR	FR-4	180	340	4.01	0.02	V-0
370HR	FR-4	180	340	4.04	0.021	V-0
Astra MT77	Polyimide	200	360	3	0.0017	V-0
FR402	FR-4	140	320	4.25	0.015	V-0
FR406	FR-4	170	300	3.93	0.0167	V-0
FR408	FR-4	180	360	3.67	0.012	V-0
FR408HR	FR-4	190	360	3.68	0.0092	V-0
IS410	FR-4	180	350	3.97	0.02	V-0
IS680	Polyimide	200	360	2.80-3.45	0.0025-0.0035	V-0
P95/P25	Polyimide	260	416	3.76	0.017	V-0
P96/P26	Polyimide	260	396	3.76	0.017	V-0
Nanya						
NP-140	FR-4	140	310	4.21	0.021	V-0
NP-170TL	FR-4	170	310	4.2-4.4	0.015-0.020	V-0
NP-175FB	FR-4	170 ± 5	351	4.4-4.7	0.013-0.017	V-0
NP-175FR	FR-4	170 ± 5	351	4.4-4.7	0.013-0.017	V-0
NP-175FTL	FR-4	170 ± 5	351	4.2-4.5	0.014-0.018	V-0
Rogers						
ROG3003	Ceramic/PTFE	N/A	500	3	0.0013	V-0
ROG3006	Ceramic/PTFE	N/A	500	6.5	0.002	V-0
ROG3010	Ceramic/PTFE	N/A	500	11.2	0.0022	V-0
ROG3210	Ceramic/PTFE	N/A	500	10.8	0.0027	V-0
ROG3730		N/A	500	3	0.0016	V-0
ROG4003	hydrocarbon/ceramic	>280	425	3.55	0.0021	V-0
ROG4003C	hydrocarbon/ceramic	>280	425	3.55	0.0021	V-0
ROG4350B	hydrocarbon/ceramic	>280	390	3.66	0.0031	V-0
ROG4360	hydrocarbon/ceramic	>280	407	6.15 ± 0.15	0.0038	V-0

ROG4360G2	hydrocarbon/ceramic	>280	407	6.15 ± 0.15	0.0038	V-0
ROG5870	PTFE		500	2.33	0.0005	V-0
ROG5880	PTFE		500	2.2	0.0004	V-0
ROG6002	Ceramic/PTFE		500	2.94	0.0012	V-0
ROG6010	Ceramic/PTFE		500	10.7	0.0023	V-0
ROG6035HTC	Ceramic/PTFE			3.6	0.0013	V-0
We also provide:	BERGQUIST (Henkel)	Insulated Metal Substrates				
	ARLON	Laminate				
	TECONIC	Laminate				
	NELCO	Laminate				
	OHMEGA	OhmegaPly				
	DUPONT	Pyralux Laminates				